Formula CFB

PRODUCT DATA SHEET

Technical specifications

Property	Test Method	Unit	Tolerance	45	53	60	75	90
Substance	ISO 536	g/m²	±4%	45	53	60	75	90
Thickness	ISO 534	µm	±4	64	72	77	90	114
Opacity	ISO 2471	%	±4	77	79	81	88	91
Relative humidity	TAPPI T502 OM-89	%	±5	43	43	43	43	43
Curl	TAPPI T427 UM-85	mm	(4.0)-0.0	-2.0	-2.0	-2.0	-2.0	-2.0

GUARANTEES:

20 years legibility of the copy under normal conditions of storage (T: 15-25 ºC and 50-60% RH).

5 years shelf life under normal conditions of storage and with the original packaging.

Values are subject to change without notice.

Last update: 07/03/2019

Lecta Main Operational Offices
Llull, 331 - 08019 Barcelona – SPAIN

Tel: (+34) 93 482 10 00
Fax: (+34) 93 482 11 70