

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m ²	100			
Caliper	ISO 534	μm	106			
Gloss Gardner	ISO 8254-1	%	18			
Brightness ISO	ISO 2470 (D65)	%	95			
Opacity ISO	ISO 2471	%	90			
MD Tensile Strength	ISO 1924-1/2	KN/m	4,6			
CD Tensile Strength	ISO 1924-1/2	KN/m	3,7			
Tearing strength MD	ISO 1974	mN	600			
Tearing strength CD	ISO 1974	mN	660			
Cobb 60 back side	ISO 535	g/m ²	28			

Tolerances	Ref. STD	Unit of meas.	RANGE			
Substance	ISO 536	g/m ²	96/104			
Caliper	ISO 534	μm	101/111			
Gloss Gardner	ISO 8254-1	%	14/22			
Brightness ISO	ISO 2470 (D65)	%	93/97			
Opacity ISO	ISO 2471	%	88/92			
MD Tensile Strength	ISO 1924-1/2	KN/m	3.9/5.3			
CD Tensile Strength	ISO 1924-1/2	KN/m	3.1/4.2			
Tearing strength MD	ISO 1974	mN	510/690			
Tearing strength CD	ISO 1974	mN	560/760			
Cobb 60 back side	ISO 535	g/m ²	24/32			

Notes:

Finishing **Embossed**
 Printing method **Sheet-fed offset**
 Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.