

Europapier
Autokaderstr 86 - 96
A - 1211 Wien
AUSTRIA

8th June 2009

Product Specification :

COST01.. / COST01AK

Description :

Color Style

Colour :

Various

Tolerance

Grammage g/m² :

300 ± 5%

Thickness µm :

400 ± 7.5%

Burst kPa :

435 Minimum
600 Expected

Cobb (1 min) g/m² :

25 Target
35 Maximum

Bendtsen Roughness ml/min :


800-1800 Range

Moisture % :

7.5 ± 1.0

Dennison Wax Pick / Clear :

10 Minimum
14 Expected



**A P Dolan
Quality Systems Manager**

