



Technical Data Sheet

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	80 +/- 2
Thickness	ISO 534	µm	106 +/- 3
Bulk	ISO 534		1,33
Moisture content	ISO 287	%	4,4 +/- 0,6
Roughness	ISO 8791	Bendtsen ml/min	220 +/- 50
Whiteness	ISO 11475	CIE	146 +/- 3
Brightness	ISO 2470-2	%	105 +/- 1
Opacity	ISO 2471	%	92 +/- 2
Stiffness MD	ISO 2493	m/N	110 +/- 15
Stiffness CD	ISO 2493	m/N	50 +/- 15



References:

Product is made taking into account requirements of DIN EN 12281
Product made from ECF Pulp

Sylvamo France SA

Usine de Saillat
87720 Saillat sur Vienne, France
Extract date: March 2022

The data presented can be changed without notice.