

TECHNICAL DATA SHEET

Office Premium Cut-Size

Physical Parameters

| | REFERENCE | TARGET | TYPICAL | _ VA | LUES |
|--------------------------------|-----------------|--------|---------|------|------|
| Basis Weight, g/m ² | ISO 536 | 90.0 | 86.4 | | 93.6 |
| Thickness, µm | ISO 534 | 112 | 108 | | 116 |
| Stiffness MD, mN | ISO 2493-1 | | ≥ 140 | | |
| Stiffness CD, mN | ISO 2493-1 | | ≥ 70 | | |
| Tensile MD, kN/m | ISO 1924-2 | | ≥ 4.8 | | |
| Bendtsen Roughness, ml/min | ISO 8791-2 | 140 | 100 | | 180 |
| Air Permeability, ml/min | ISO 5636-3 | | | ≤ | 1700 |
| Moisture, % | ISO 287 | 4.0 | 3.5 | | 4.5 |
| Formation, # | Internal Method | | ≥ 50 | | |

Optical Parameters

| | REFERENCE | TARGET | TYPICAL VALUES | |
|-------------------|------------|--------|----------------|-----|
| Whiteness, CIE | ISO 11475 | 169 | 166 | 172 |
| Brightness D65, % | ISO 2470-2 | 112 | 109 | 115 |
| Opacity, % | ISO 2471 | 96 | ≥ 94 | |

The product specifications provided hereby can be changed on one or more parameters at any time by The Navigator Company

Approved by:

Technical Department: Eng. Cidália Torre Abreu

Printed on: 2023/03/13 09:32:13



QUALITY AND ENVIRONMENTAL INFORMATION

- The Navigator Company's papers are made from Elemental Chlorine Free (ECF) bleached kraft pulp;
- The Navigator Company's papers are produced in a neutral/slightly alkaline papermaking process, therefore considered as "acid free" products which meet the requirements of ISO 9706 standard, "Information and documentation – Paper for documents – Requirements for permanence";
- The Navigator Company's laboratories are accredited according to the ISO 17025 standard;
- Quality, Environmental and Safety Management Systems are certified according to the ISO 9001, ISO 14001 and OHSAS 18001 standards.
- The Navigator Company is chain-of-custody certified according to standards FSC-STD-40-004 and FSC-STD-50-001 (NC-COC/CW-014433) and to standard PEFC ST 2002:2010 (APCER/2007/CDR.0008).