# **JAC GRAPHICS JAC OPAQUE FS**

## **Print carrier**

## Average values

JAC® OPAQUE is a range of opaque self-adhesive papers for re-labelling applications where the existing texts must be completely concealed, e.g. for text or price corrections. These self-adhesive papers display excellent opacity.

JAC® SCRIPT OPAQUE FSC A calendared, white writing paper displaying very good printing properties. The face material is made from FSC® certified paper (FSC MIX CREDIT CU-COC-807907).

JAC® CHROMO GLOSS OPAQUE FSC A specially coated, white, gloss paper which is particularly suitable for multi-colour labels. The face material is made from FSC® certified paper (FSC MIX CREDIT CU-COC-807907).

JAC® CHROMO MATT OPAQUE FSC A specially coated, white, matt paper which is particularly suitable for the multi-colour offset printing of high-quality labels. The face material is made from FSC® certified paper (FSC MIX CREDIT CU-COC-807907).

	SCRIPT OPAQUE FSC	CHROMO GLOSS OPAQUE FSC	CHROMO MATT OPAQUE FSC
Weight (g/m²)	86	102	103
Thickness (µm)	85	100	100
Opacity (%)		98	
Shelf life of laminate <sup>1)</sup> (years)	2	2	2

<sup>1)</sup> Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%

For information regarding EHS regulation please visit our website under downloads "Guidelines for Use "5.12 Product Compliance JAC® Offset"

For technical guidance please visit our web side under downloads "Guidelines for use "- Offset printing

#### **Adhesive**

### Average values

DURO D 2000 is a dispersion-based permanent acrylic adhesive displaying very good processing properties and excellent guillotining behaviour. Its good adhesion permits use on a diversity of surfaces, such as paper, steel, glass etc. It also displays very good UV stability.

	D2000	
Adhesion (N/25 mm) (FTM 2 on st.steel/20 min. bond time)	9.2	
Tack (N/25 mm) (FTM 9 on glass)	9.6	
Recommended minimum application temperature (°C)	> +5	
Heat resistance up to 24 hrs (°C) up to 1 hr (°C)	+80 +110	
Resistance to cold (°C) 1) down to	- 40	

<sup>1)</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs

B 85

78

82

**B** 110

86

87

## Silicone paper

## Average values

**B 85** – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized through a special coating on one side. B85 displays high dimensional stability and excellent flatness.

(available ex stock with Chromo Gloss Opaque FSC).

**B 110** – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized and displays very high dimensional stability and excellent flatness.

(All grades available ex stock)

**Guarantee and liability** Issue December 2016

All Avery Dennison and JAC® statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and JAC® products are sold with the understanding that purchaser has independently determined the suitability of such products for its

All Avery Dennison and JAC® products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com

Weight (g/m<sup>2)</sup>

Thickness (µm)

