

Print carrier

Average values

JAC® TAG FSC is white, wood-free, supercalendered board. It enjoys application wherever a face material of particularly high stability is required. The face material is made from FSC® certified paper (FSC MIX CREDIT CU-COC-807907).

	TAG FSC
Weight (g/m ²)	170
Thickness (µm)	150
Surface smoothness (PPS 10)	2.8 µm
Opacity (%)	98
Shelf life of laminate ¹⁾ (years)	2

¹⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%

For technical guidance please visit our website under Downloads "Guidelines for use" – Offset printing

For information regarding EHS regulation please visit our website under downloads "Guidelines for Use" 5.12 Product Compliance Jac® Offset"

Adhesive

Average values (measured on glass)

DURO PLUS is an acrylic dispersion-based adhesive, displaying very good application and processing properties including good to excellent guillotining behaviour and very good UV stability.

It shows good performance on rough and plastic substrates.

	DURO PLUS
Adhesion (N/25 mm) (FTM 2 on st. steel/20 min. bond time)	11
Tack (N/25 mm) (FTM 9 on glass)	15.4
Recommended minimum application temperature (°C)	> +5
Heat resistance up to 24 hrs (°C) up to 1 hr (°C)	+80 +110
Resistance to cold (°C) ¹⁾ down to	- 40

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs

Silicone paper

Average values

B 110 – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized and displays very high dimensional stability and excellent flatness.

	B 110
Weight (g/m ²)	86
Thickness (µm)	87

Guarantee and liability

Issue December 2016

All Avery Dennison and JAC® statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and JAC® products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All Avery Dennison and JAC® products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



www.jacgraphics.com